

ECISS
EUROPEAN COMMITTEE FOR IRON AND STEEL STANDARDISATION
COMITÉ EUROPÉEN DE NORMALISATION DU FER ET DE L'ACIER
EUROPÄISCHES KOMITEE FÜR EISEN-UND STAHLNORMUNG
EUROPEAN CERTIFIED REFERENCE MATERIAL (EURONORM – CRM)

CERTIFICATE OF CHEMICAL ANALYSIS

EURONORM – CRM No. 691-1, IRON ORE

LABORATORY MEANS (4 values) - Mass content in % related to the dried (105 °C) sample

Line No	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	V	Cr	Ni	C
1	64.10	0.5325	---	---	0.4532	0.9295	0.1654	0.0813	0.0581	0.0138	0.0446	0.0552	0.0080	0.0265	---
2	64.12	0.5384	0.9652	1.9448	0.4538	0.9439	0.1677	0.0820	0.0592	0.0139	0.0455	0.0554	0.0083	0.0281	0.2899
3	64.14	0.5385	0.9776	1.9494	0.4583	0.9443	0.1678	0.0831	0.0608	0.0142	0.0473	0.0570	0.0087	0.0283	0.2982
4	64.15	0.5411	0.9840	1.9691	0.4606	0.9469	0.1689	0.0845	0.0608	0.0145	0.0482	0.0584	0.0087	0.0284	0.2988
5	64.16	0.5505	0.9849	1.9989	0.4612	0.9470	0.1699	0.0849	0.0610	0.0147	0.0489	0.0584	0.0090	0.0286	0.3008
6	64.21	0.5514	0.9873	2.0040	0.4636	0.9486	0.1703	0.0873	0.0614	0.0155	0.0497	0.0587	0.0090	0.0288	0.3011
7	64.27	0.5523	0.9894	2.0065	0.4638	0.9523	0.1712	0.0878	0.0643	0.0163	0.0500	0.0589	0.0090	0.0291	0.3020
8	64.27	0.5588	0.9904	2.0067	0.4682	0.9555	0.1712	0.0878	0.0644	0.0165	0.0500	0.0592	0.0092	0.0293	0.3064
9	64.29	0.5614	0.9917	2.0208	0.4722	0.9575	0.1718	0.0882	0.0648	0.0170	0.0506	0.0597	0.0098	0.0295	0.3069
10	64.36	0.5614	0.9917	2.0228	0.4726	0.9624	0.1724	0.0889	0.0650	0.0173	0.0511	0.0597	0.0100	0.0298	0.3097
11	64.37	0.5629	0.9980	---	0.4739	0.9640	0.1724	0.0896	0.0653	0.0189	0.0514	0.0604	0.0101	0.0300	0.3112
12	64.41	0.5634	0.9993	2.0278	0.4776	0.9694	0.1733	0.0900	0.0664	0.0190	0.0516	0.0610	0.0105	0.0302	0.3165
13	64.42	0.5671	0.9995	2.0350	0.4794	0.9785	0.1739	0.0900	0.0666	0.0191	0.0517	0.0623	0.0105	0.0303	0.3252
14	64.45	0.5693	1.0028	2.0397	0.4803	0.9806	0.1750	0.0902	0.0672	0.0192	0.0520	0.0631	0.0110	0.0305	0.3288
15	64.45	0.5700	1.0045	2.0550	0.4836	0.9837	0.1759	0.0904	---	---	0.0525	0.0632	0.0111	0.0314	---
16	64.53	0.5701	---	2.0558	0.4869	0.9859	0.1765	0.0905	---	---	0.0529	0.0641	---	0.0316	---
17	64.64	---	1.0217	2.0592	0.4933	0.9865	0.1779	0.0910	---	---	0.0533	0.0650	---	---	---
18	64.67	---	1.0285	2.0705	0.4960	0.9903	0.1795	0.0917	---	---	0.0561	0.0664	---	0.0334	---
19	64.69	---	1.0289	2.1035	0.4986	0.9918	0.1827	---	---	---	---	---	---	0.0346	---
20	64.69	---	1.0292	---	0.5063	1.0012	0.1837	---	---	---	---	---	---	---	---
21	64.70	---	---	---	---	---	---	---	---	---	---	---	---	---	---
M_M	64.39	0.5556	0.9992	2.0217	0.4752	0.9660	0.1734	0.0877	0.0632	0.0164	0.0504	0.0603	0.0095	0.0299	0.3073
S_M	0.21	0.0125	0.0180	0.0422	0.0154	0.0202	0.0049	0.0033	0.0030	0.0021	0.0029	0.0032	0.0010	0.0020	0.0111
S_W	0.10	0.0063	0.0084	0.0122	0.0070	0.0061	0.0024	0.0016	0.0014	0.0009	0.0012	0.0010	0.0005	0.0005	0.0040

Line No	Zn	Pb	Cu	Fe (II)	Ba	Ce	Sr	Zr	GOI ⁽¹⁾
1	0.0154	0.0006	---	---	0.0060	0.0030	0.0143	0.0104	---
2	0.0158	0.0007	---	20.54	0.0064	0.0030	0.0149	0.0122	1.28
3	0.0164	0.0007	0.0726	20.58	0.0065	0.0048	0.0157	0.0123	1.30
4	0.0165	0.0007	0.0728	20.64	0.0068	0.0051	0.0160	0.0141	1.31
5	0.0168	0.0008	0.0752	20.66	0.0071	0.0059	0.0163	0.0142	1.35
6	0.0173	0.0008	0.0764	20.67	0.0072	---	0.0177	0.0145	1.35
7	0.0180	0.0008	0.0765	20.77	0.0075	---	0.0178	---	1.44
8	0.0181	0.0009	0.0766	20.78	0.0082	---	---	---	1.44
9	---	0.0011	0.0768	20.79	---	---	---	---	1.46
10	0.0185	0.0011	0.0769	20.83	---	---	---	---	1.47
11	0.0190	---	0.0772	20.86	---	---	---	---	1.50
12	0.0198	---	0.0773	---	---	---	---	---	---
13	0.0209	---	0.0774	---	---	---	---	---	1.52
14	0.0216	---	0.0780	---	---	---	---	---	1.55
15	0.0216	---	0.0782	---	---	---	---	---	1.56
16	0.0220	---	0.0782	---	---	---	---	---	---
17	0.0221	---	0.0794	---	---	---	---	---	---
18	0.0222	---	0.0796	---	---	---	---	---	---
19	0.0225	---	---	---	---	---	---	---	---
20	0.0227	---	---	---	---	---	---	---	---
21	0.0233	---	---	---	---	---	---	---	---
M_M	0.0195	0.0008	0.0768	20.71					
S_M	0.0027	0.0002	0.0020	0.11					
S_W	0.0008	0.0001	0.0010	0.05					

M_M: Mean of intralaboratory means

S_M: Standard deviation of intralaboratory means

S_W: Intralaboratory standard deviation

The laboratory mean values have been examined statistically to eliminate outlying values.

Where a "----" appears in the table it indicates that an outlying value has been eliminated by either the Cochran or Grubbs Test.

Values given in *italic* are for information only.

(1) GOI = Gain On Ignition
(negative Loss On Ignition)

Additional values for information (in µg/g):

As: 0.6; B: 3.2; Be: < 0.1; Cd: < 0.1; Co: 216; Cs: < 0.1; Ga: 21; Hf: 4.7; La: 25; Li: 0.9; Mo: 1.1; Nb: 12; Nd: 32; Rb: 2; Sb: < 0.1; Sc: 46; Sn: 21; Ta: 2; Te: < 0.1; Th: 15; U: 4.2; Y: 5.4

CERTIFIED VALUES - Mass content in %

	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na
M_M	64.39	0.556	0.999	2.022	0.475	0.966	0.1734	0.0877	0.0632	0.0164
C(95 %)	0.10	0.007	0.009	0.022	0.008	0.010	0.0023	0.0017	0.0017	0.0012

	K	V	Cr	Ni	C	Zn	Pb	Cu	Fe (II)
M_M	0.0504	0.0603	0.0095	0.0299	0.307	0.0195	0.0008	0.0768	20.71
C(95 %)	0.0014	0.0016	0.0006	0.0010	0.007	0.0013	0.0002	0.0011	0.08

The half-width confidence interval $C(95\%) = \frac{t \times S_M}{\sqrt{n}}$ where "t" is the appropriate Student's t value and "n" is the number of acceptable mean values

For further information regarding the confidence interval for the certified value see ISO Guide 35:2006 sections 6.1 and 10.5.2

This certified reference material was prepared in accordance with the recommendations set out in ISO Guides 30 – 35 and issued by:



ArcelorMittal Maizières Research SA (formerly "IRSID")

Voie Romaine, BP 30320, F-57283 Maizières-lès-Metz Cedex

On behalf of: The Iron and Steel Nomenclature Co-ordinating Committee (COCOR) of the ECISS, after approval by all the participating laboratories and all the producing organisations (France - ArcelorMittal Maizières Research SA & CTIF; Germany - Iron and Steel CRM Working Group: Stahlinstitut VDEh, Bundesanstalt für Materialforschung und -prüfung (BAM) & MPI für Eisenforschung; Nordic Countries - Nordic CRM Working Group).

Certificate updated February 2018 (mention of preliminary drying)
Replaces the original certificate dated June 2017

METHODS USED		
Element	Line number	Methods
Fe	1.2.3.4.5.6.8.9.10.13.14.15.20.21	Titration with Cr (VI) after reduction with Sn (II)
	12 7.11.16.17.18.19	Titration with Cr (VI) after reduction with Ti (III) XRF
Si	1.4.12	ICP-OES
	2	Gravimetry, dehydration with hydrochloric acid
	3.5.8.11.13.15	XRF
	6	FAAS
	7	Gravimetry, dehydration with sulphuric acid
	9	Gravimetry, dehydration with hydrochloric acid in presence of gelatine
Ca	10.16	Gravimetry, dehydration with perchloric acid
	14	ICP-MS
	2	ICP-MS
	3.5.9.10.11.14.15.20	XRF
	4	Complexometric titration, visual end point
Mg	6.7.13.16.18.19	ICP-OES
	8.12.17	FAAS
	2.5.6.8.13.15.16.17	ICP-OES
	3.4.9.10.12.14.19	XRF
Al	7.18	FAAS
	1	FAAS, without separation
	2.6.11.14.16.17.19.20	XRF
Ti	3.4.5.7.9.10.12.13.15.18	ICP-OES
	8	ICP-MS
	1.2.3.9.10.11.14.15.18	ICP-OES
	4.6.7.8.12.13.16.19.20	XRF
Mn	5	FAAS
	17	ICP-MS
	1.3.4.5.8.10.11.14.17	ICP-OES
	2.7.18.20	FAAS
	6.9.12.15.16.19	XRF
P	13	ICP-MS
	1.2.6.8.10.12.16	XRF
	3.17	ICP-MS
	4.7.9.11.14.15	ICP-OES
	5	Spectrophotometry, molybdenum blue, without extraction
S	13.18	Spectrophotometry, phosphovanadomolybdate, extraction
	1	Combustion, Oxidation reduction titration
	2.4.5.6.7.8.10.12.13.14	Combustion, Infrared absorption
	3	XRF
Na	9	ICP-MS
	11	ICP-OES
	1.2.9.11	ICP-OES
	3.4.5.7.10.13.14	FAAS
K	6.8	ICP-MS
	12	XRF
	1.7.12.13.15.17	FAAS
	2.3.8.18	XRF
V	4.9.10.11.14.16	ICP-OES
	5.6	ICP-MS
	1.13.15	ICP-MS
	2.3.5.6.7.9.11.12.16.18	ICP-OES
	4.10.14.17	XRF
Cr	8	FAAS
	1.3.4.6.9.11.12.13	ICP-OES
	2.10	XRF
	5.7.8.15	ICP-MS
Ni	14	FAAS
	1.2	FAAS
	3.4.5.6.7.8.10.13.15.19	ICP-OES
	9.11.14.16	ICP-MS
C	12.18	XRF
	2.14	Combustion, Gravimetry
	3.4.5.6.7.8.9.10.11.12	Combustion, Infrared absorption
	13	Combustion, Gas volumetry
Zn	1.7.11.20	ICP-MS
	2.3.4.6.12.18.21	ICP-OES
	5.8.10.13.16.19	FAAS
	14.15.17	XRF
Pb	1.2.3.5.6.10	ICP-MS
	4	ETAAS
	7.8.9	ICP-OES
Cu	3.4.7.10.12.15.16.17	ICP-OES
	5.9.11	FAAS
	6.14	XRF
	8.13.18	ICP-MS
Fe (II)	2	Titration with Cr (VI) in the residue of the dissolution in ferric-chloride medium
	3	Titration with Cr (VI) in the residue of the dissolution in bromine-methanol medium
	4.5.7.8.9.11	Titration with Cr (VI) after hydrochloric acid dissolution under CO ₂
	6	Titration with Cr(VI) after sulfuric/hydrofluoric dissolution
	10	Titration with Mn (VII) after hydrochloric acid dissolution under CO ₂
Ba	1.3.6.8	ICP-OES
	2.4.5.7	ICP-MS
	9	XRF
Ce	1.2	ICP-OES
	3.4.5	ICP-MS
Sr	1.2.4.6	ICP-MS
	3.5.7	ICP-OES
Zr	1.2.3.6	ICP-MS
	4.5	ICP-OES
GOI	1	Combustion at 1100°C, Gravimetry
	2	Combustion at 950°C, Gravimetry
	3.4.5.7.8.9.11.12.14.15	Combustion at 1000°C, Gravimetry
	6	Combustion at 1050°C, Gravimetry
	10.13	Combustion at 900°C, Gravimetry

Abbreviations:

ETAAS Electrothermal Atomic Absorption Spectrometry
FAAS Flame Atomic Absorption Spectrometry
ICP-MS Inductively Coupled Plasma – Mass Spectrometry

ICP-OES
XRF

Inductively Coupled Plasma – Optical Emission Spectrometry
X-Ray Fluorescence

DESCRIPTION OF THE SAMPLE

The sample is available in the form of a powder passing a nominal 100 µm aperture. It is supplied in bottles containing 100 g.

INTENDED USE & STABILITY

ECRM 691-1 is intended for the verification of analytical methods, such as those used by the participating laboratories, for the calibration of analytical instruments in cases where the calibration with primary substances (pure metals or stoichiometric compounds) is not possible and for establishing values for secondary reference materials.

It will remain stable provided that the bottle remains sealed and is stored in a cool, dry atmosphere. When the bottle has been opened the lid should be secured immediately after use. If the content should become discoloured (e.g. oxidised) due to atmospheric contamination it should be discarded.

TRACEABILITY

The traceability of ECRM 691-1 has been established in accordance with principles of ISO Guides 30 – 35 and the International vocabulary of basic and general terms in metrology.

The assigned values for each material are achieved by inter-laboratory characterization, each laboratory using the method of their choice, details of which are given above. These methods are either stoichiometric analytical techniques or methods which are calibrated against pure metals or stoichiometric compounds. Most methods used were either international or national standard methods or methods which are technically equivalent.

PARTICIPATING LABORATORIES

AG der Dillinger Hüttenwerke, Dillingen/Saar (Germany)
 ALS Scandinavia AB, Luleå (Sweden)
 ArcelorMittal Asturias, Avilés (Spain)
 ArcelorMittal Atlantique et Lorraine, Dunkerque (France)
 ArcelorMittal Atlantique et Lorraine, Florange (France)
 ArcelorMittal Dofasco, Hamilton (Canada)
 ArcelorMittal Eisenhüttenstadt Forschungs- und Qualitätszentrum GmbH, Eisenhüttenstadt (Germany)
 ArcelorMittal Fos, Fos-sur-Mer (France)
 ArcelorMittal Maizières Research SA, Maizières-lès-Metz (France)
 British Steel Testing Solutions, Scunthorpe (UK)
 Bundesanstalt für Materialforschung und -prüfung (BAM), Berlin (Germany)
 Claisse, Quebec (Canada)
 Degerfors Laboratorium AB, Degerfors (Sweden)
 FSUE VIMS, Moscow (Russia)
 Höganäs Sweden AB, Höganäs (Sweden)
 ICRM, Yekaterinburg (Russia)
 ISD Dunafer Zrt., Dunaújváros (Hungary)
 Luxcontrol, Esch-sur-Alzette (Luxembourg)
 Max-Planck Institut für Eisenforschung GmbH, Düsseldorf (Germany)
 Pattinson & Stead (2005) Ltd., Middlesbrough (UK)
 Ridsdale & Co. Ltd., Middlesbrough (UK)
 SARM-CRPG-CNRS, Vandoeuvre-lès-Nancy (France)
 SSAB Europe Oy, Raahе (Finland)
 Tata Steel IJmuiden, IJmuiden (Netherlands)
 Techlab, Metz (France)
 ThyssenKrupp Steel Europe AG, Duisburg (Germany)
 voestalpine Stahl GmbH, Linz (Austria)

FURTHER INFORMATION

Pour disposer d'informations sur la fabrication, la certification et la distribution des Matériaux de Référence Certifiés Européens (EURONORM-MRC) ainsi que sur l'utilisation des informations statistiques données sur ce certificat, se reporter soit au producteur de ce Matériau de Référence Certifié, soit aux Rapports Techniques CEN/TR 10317:2014 et CEN/TR 10350:2013. On peut se procurer ces deux documents auprès des organismes nationaux de normalisation. (Pour la France: AFNOR, 11 Avenue Francis de Pressensé, 93571 – St Denis la Plaine Cedex).

D'autres informations et avis au sujet de ce Matériau de Référence Certifié, ou de tout autre Matériau de Référence Certifié ou Matériau de Référence produit par ArcelorMittal Maizières Research SA, peuvent être demandés en contactant l'adresse figurant dans le bas de ce Certificat.

For information regarding the preparation, certification and supply of these European Certified Reference Materials (EURONORM-CRMs) and the use of the statistical information given on this certificate, please refer either to the producer of this Certified Reference Material or to Technical Reports CEN/TR 10317:2014 and CEN/TR 10350:2013, both of which are available from the national standards body in your country. (In the UK this is the BSI, 389 Chiswick High Road, London W4 4AL).

Further information and advice on this or other Certified Reference Materials or Reference Materials produced by ArcelorMittal Maizières Research SA, may be obtained from the address below.

Angaben über Herstellung, Zertifizierung und Bezugsmöglichkeiten dieser Europäischen Zertifizierten Referenzmaterialien (EURONORM-ZRM) sowie über die Anwendungen der in diesem Zertifikat enthaltenen statistischen Daten sind erhältlich beim Hersteller dieses zertifizierten Referenzmaterials, dessen Adresse auf diesem Zertifikat angegeben ist oder sie finden sich in den CEN-Reports CEN/TR 10317:2014 und CEN/TR 10350:2013, beide zu beziehen durch die nationalen Normenorganisationen (in Deutschland bei der Vertriebsstelle des DIN: Beuth-Verlag GmbH, Burggrafenstraße 4-10, 10787 Berlin).

Weitere Informationen und Hinweise zu diesem oder anderen durch ArcelorMittal Maizières Research SA hergestellten zertifizierten Referenzmaterialien oder Referenzmaterialien können unter der unten angegebenen Adresse erhalten werden.

För information angående tillverkning, certifiering och anskaffning av dessa europeiska certifierade referensmaterial (EURONORM CRM) och för användning av statistisk information, som angivits i detta certifikat, refereras antingen till producenten av detta certifierade referensmaterial eller till Teknisk Rapport CEN/TR 10317:2014 och CEN/TR 10350:2013 som kan erhållas från den nationella standardiseringsorganisationen. (Sverige: SIS, Swedish Standards Institute, Box 45443, 104 31 Stockholm, Finland: SFS, PL. 116, FIN-002 41, Helsingfors, Danmark: DS, Kollegievej 6, DK-Charlottenlund 2920, Norge: NSF, Drammensveien, 145 A, Postboks 353 Skøyen, NO-0213 Oslo, Island: STRI, Holtagardar, IS-104 Reykjavik).

Ytterligare information och rådfrågan om detta eller andra Certifierade Referensmaterial/Referensmaterial, producerade av ArcelorMittal Maizières Research SA, kan erhållas från angiven adress enligt nedan.

Laurence DAHERON
Responsible for certification

ArcelorMittal Maizières Research SA
Voie Romaine
BP 30320
57283 Maizières-lès-Metz Cedex
France

E-mail: reference.materials@arcelormittal.com
Website: referencematerials.arcelormittal.com