

REFERENCE MATERIAL IR 1741

Low alloy steel

SOLD OUT

LABORATORY MEANS – Mass content in %

Element	Si	Mn	P	Mo	Ni	Cu	Sn	V
M_M	0.380	0.466	0.037	0.204	0.962	0.117	0.059	0.051
s_M	0.012	0.012	0.004	0.012	0.026	0.008	0.004	0.004

<i>Element</i>	<i>C</i>	<i>Al</i>	<i>Ti</i>
M_M	<i>0.244</i>	<i>0.102</i>	<i>0.049</i>

M_M : Mean of the intralaboratory means

s_M : Standard deviation of the intralaboratory means

The laboratory mean values have been examined statistically to eliminate outlying values.
Values given *in italic* are for information only.

The material is available in the form of a 38mm dia. x 25mm disc.

This Reference Material was prepared by:

INSTITUT DE RECHERCHES DE LA SIDÉRURGIE (IRSID)

Certificate revised August 2016 (previous issue August 1999)

ArcelorMittal Maizières Research SA (formerly "IRSID")
Voie Romaine, BP 30320, F-57283 Maizières-lès-Metz Cedex

✉ E-mail: reference.materials@arcelormittal.com

Website: referencematerials.arcelormittal.com